

## Catalyst

### АОК-75-60

Alumina-supported manganese oxide monolithic catalyst for CO and VOC complete oxidation. Applied for emission treatment of enterprises processing wood and producing slab materials (chipboard, plywood), as well as various chemical industries.

#### Specification:

№ Parameter	Standard value
1. Shape	Regular quadrangular prism
2. Color	Light brown, grey shade is allowed
3. Size, mm: - Length of the base side - Wall thickness	100±3 50±1,5 0.8±0.2
4. Bulk density, g/cm <sup>3</sup>	0.80±0.15
5. Mechanical compressive strength for fragments 10x10x10 mm, MPa: - to side wall - to the end wall	>2.0 >6.0
6. Number of channels per square inch (CPSI), pcs	100